

TDS – Techniwax P9830

Information

Product Description

Techniwax P9830 is a fully refined micro wax with a variety of industrial applications.

Physical Properties

Test	Method	Specification	Typical
Congealing Point °C	(ASTM D938)	83 - 88	85
Viscosity @ 100°C	(ASTM D445)	13 - 18	16 cSt
Penetration @ 25°C	(ASTM D1321)	12 Max	10 dmm
Penetration @ 43.3°C	(BS 1426)	50 Max	41 dmm
Colour	(ASTM D1500)	0.5 Max	<0.5
Colour	(ASTM D156)	10 Min	12

Statement

- Formulated from materials whose refining history is fully traceable.
- Does not contain or come into contact with any animal or GMO products at any stage of its manufacture.
- Does not contain residual solvents as per guidelines CPMP/ICH283/95.
- Has not been tested on animals by ourselves or on our behalf.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users must make their own tests to determine the suitability of these products for their own particular purposes. The company makes no warranty of any kind, expressed or implied, including those of merchantability or fitness for a particular purpose, other than that the material conforms to its applicable current Standard Specifications.